



Environmentally Safe Polymers, Inc.

Technical Data

Updated 11/2004

POLYDECK #57 BATCH MIX ALIPHATIC ELASTOMER

PRODUCT DESCRIPTION AND USAGE:

PolyDeck #57 is a two component, one to one by volume, batch mix aliphatic polyurethane coating that has a long pot life and moderate tack free time. PolyDeck #57 is designed for use as a colorfast wearing and waterproofing membrane for pedestrian decks, auto decks, industrial flooring and roofing.

COLOR:

Standard color for PolyDeck #57 is white. Custom colors are also available. Contact your E.S.P. Representative for more information on custom colors.

PHYSICAL PROPERTIES

CHEMICAL RESISTANCE:

Good hydrolytic stability up to 160°F. Water resistance is excellent. Good resistance to acids and hydrocarbon solvents. Fair resistance to oxygenated solvents, chlorinated solvents, and inorganic bases.

TENSILE:

ASTM D-412
Strength: 2500 psi
Elongation: 400%
Permanent Set: 15% maximum

HARDNESS:

ASTM D-2240
Shore A 80 ± 3

TEAR RESISTANCE:

ASTM D-624
Die C 250 pli

ABRASION RESISTANCE:

Excellent.

LIQUID PROPERTIES

COVERAGE:

Sq. Ft./Gal./Mil 1280

SOLIDS:

Weight: 85%
Volume: 80%

VISCOSITY:

Poly Component: Semi-fluid thixotropic liquid.
Iso Component: 300-400 cps @ 77°F.

DENSITY:

Poly Component: 11-12 lbs./gal. (S.G. 1.32-1.44)
Depending on color.

Iso Component: 8.16 lbs./gal. (S.G. 0.98)

FLASH POINT:

Above 81°F T.O.C.

TOXICITY:

Contains solvent that requires ventilation during application. Contains polyisocyanate that may be irritating to the skin and is toxic if inhaled as particulate matter. Material contacting the skin should be neutralized by washing with generous amounts of water.

STORAGE STABILITY:

One year in unopened original containers at 40-90°F. Normally containers should be used within one week after opening.

APPLICATION

MIXING:

Best results are obtained by pouring the Iso into the mixing container first. Then mix an equal volume of Polyol into the Iso.

POT LIFE:

Pot life of a one gallon quantity is 45 minutes at 70°F. Higher temperatures and larger quantities will shorten pot life. Lower temperatures and smaller quantities will lengthen pot life.

CURE TIME:

PolyDeck #57 will be ready for recoat in 12 hours at 70°F and 24 at 40°F. Allow 72 hours after final coat at 70°F before permitting traffic.

EQUIPMENT:

PolyDeck #57 can be applied by notched trowel, medium nap roller, squeegee or brush.

Our data is based on information from lab and field testing which we believe to be reliable and accurate. Environmentally Safe Polymers, Inc. makes no warranties, expressed or implied of the products use or its results, and assumes no obligation or liability in connection therewith.